



DESCRIPTION

Insulfrax Blok products are manufactured using a combination of mineral wool and Insulfrax alkaline earth silicate wool, blended with specially selected inorganic and organic binders to give thick, rigid boards with exceptional characteristics. Insulfrax Blok is designed specifically for use as back-up insulation in various high temperature industry applications. Insulfrax Blok is available in two grades, Blok 80 is suitable for use in applications with operating temperatures up to 800°C and Blok 110 for applications with operating temperatures up to 1100°C.

GENERAL CHARACTERISTICS

Insulfrax Blok products have the following outstanding characteristics:

- High temperature stability
- Low thermal conductivity
- Resistance to thermal shock
- Good handling strength
- Easy to cut with standard tools

TYPICAL APPLICATIONS

Refractory back-up

- Chemical processing industries
- Ferrous & non-ferrous metal industries
- Power Generation
- Ceramic Industry

Any new and/or special use of these products, whether or not in an application listed in our literature, must be submitted to our technical department for their prior written approval.

*Start saving energy now.
Contact your local distributor.*

Unifrax Ltd.

T:+44 (0)1744 88 7600

F:+44 (0)1744 88 9916

www.unifrax.com



TYPICAL PRODUCT PARAMETERS

Insulfrax Blok	80	110
Typical Chemical Analysis (fibre wt. %)		
SiO ₂	48.0 - 55.0	41.0 - 50.0
CaO	28.0 - 35.0	29.0 - 36.0
MgO	4.0 - 7.0	4.0 - 7.0
Al ₂ O ₃	8.0 - 11.0	12.0 - 16.0
Fe ₂ O ₃ + TiO ₂	<1.0	<1.5
Trace	<1.5	<1.5
Physical Properties		
Colour	Tan / Brown	Tan / Brown
Melting Point (°C)	>1230	>1230
Product Density (kg/m ³)	300	300
Use Limit (°C) *	800	1100
Loss on Ignition (wt.%)	<7.0	<7.0
Thermal Conductivity (W/mK)		
Mean Temp.		
200 °C	0.05	0.05
400 °C	0.08	0.08
600 °C	0.13	0.13
Permanent Linear Shrinkage (%) 24 Hour Soak		
800 °C	<4	-
1100 °C	-	<4

*Use limit refers to the maximum short term temperature limit. The maximum continuous use limit for boards depends upon application conditions. For certain applications continuous use temperature limits may be significantly reduced. For assistance or clarification please contact your nearest Unifrax Engineering office. Where appropriate Physical Properties data measured according to EN 1094-1.

AVAILABILITY

Thickness (mm)	80	110	Sheets per pallet
	Sheet Dimensions		1250 x 1000mm
25	✓	✓	44
40	✓	✓	22
50	✓	✓	22

Other thicknesses / sizes may be available on request subject to minimum order requirements
Water repellent versions are also available subject to order.

HANDLING INFORMATION

A Material Safety Data Sheet has been issued describing the health, safety and environmental properties of this product, identifying the potential hazards and giving advice on handling precautions and emergency procedures. This must be consulted and fully understood before handling, storage or use.

Supplied by:

Information contained in this publication is for illustrative purposes only and is not intended to create any contractual obligation. Further information and advice on specific details of the products described should be obtained in writing from a Unifrax Corporation company (Unifrax España, Unifrax France, Unifrax GmbH, Unifrax Italia, Unifrax Limited, Unifrax s.r.o.). Unifrax maintains a continuous programme of product development and reserves the right to change product specifications without prior notice. Therefore, it maintains at all times the responsibility of the customer to ensure that Unifrax materials are suitable for the particular purpose intended. Similarly, insofar as materials not manufactured nor supplied by Unifrax are used in conjunction with or instead of Unifrax materials, the customer should ensure that all technical data and other information relating to such materials has been obtained from the manufacturer or supplier. Unifrax accepts no liability arising from the use of such materials. All sales made by a Unifrax Corporation company are subject to that company's Terms and Conditions of Sale, copies of which are available on request.